

Topaz Signature Endless Matt

Product characteristics

Description

Topaz Signature Endless Matt is a paint that combines an exceptionally lasting finish with the renowned historical richness of color, thanks to a breakthrough in pure acrylic chemistry. This new, effortlessly easy-to-use formulation can be painted onto walls, woodwork and metal with an appropriate primer, making it the ultimate choice for modern homes. The enriched colour experience with wide range of colours and its matt finish keep the walls everyday new looking and fresh. This multi-surface, impressively durable and our most matt finish yet also gives a smooth luxurious finish with outstanding opacity, washability, flexibility, Stain resistance and unique colour retention properties.

Recommended use

Ideal as topcoat recommended for all indoor spaces, including residential areas, villas and hotels for walls, ceilings and partitions where an absolute matt finish and colour richness desired.

Features

- Ultra matt from every angle: < 2% sheen
- Durable and scuff resistant
- Washable colours that won't leave marks when wiped
- Superior opacity.
- Excellent whiteness.
- Ultra Low VOC
- Stain resistant
- Anti bacterial and Anti fungal

Product safety

Flash point 100°C [211°F]

VOC content

Legislation	Value
EU	1 g/L [0.01 lb/US gal]
US (coatings)	2 g/L [0.02 lb/US gal]
US (regulatory)	9 g/L [0.08 lb/US gal]
Canada	2 g/L [0.02 lb/US gal]
China	1 g/L [0.01 lb/US gal]
Hong Kong	2 g/L [0.02 lb/US gal]
Korea	1 g/L [0.01 lb/US gal]

VOC values may vary with shade, please consult the Safety Data Sheet, section 9.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

Product data

Product code

58404

Standard shade* / code

White 10000

Wide range of colours is available via Hempel's tinting system.

Gloss

Dead matt

Volume solids

44%

Specific gravity

1.5 kg/L [12 lb/US gal]

Topaz Signature Endless Matt

Reference dry film thickness

30 micron [1.2 mils]

Surface preparation

Cleanliness

- The surface must be dry and clean prior to application.

New build:

- Concrete must cure completely; for 28 days minimum.
- Moisture content in the surface must be below 4%.
- Minor areas can be sanded/abraded to obtain a uniform dense surface profile

Maintenance and Repair

- Remove dust, loose material and any other contamination.
- Surface imperfections in the substrate must be fixed/filled before paint application.
- Use compatible cementitious repair material for major surface imperfections.
- Apply primer/sealer prior to application of filler.
- Areas with filler to be sealed with primer/sealer.

Roughness

- Sand to smoothen filler.

Application

Thinner

Fresh water

Cleaner

Fresh water

Application method

Tool	Thinning max vol.	Application parameters
Brush/Roller	5%	Not Applicable.
Air spray	15%	Nozzle pressure: 3-5 bar [44 psi] Nozzle orifice: 0.07-0.086"
Airless spray	5%	Nozzle pressure: 150 bar [2200 psi] Nozzle orifice: 0.017-0.021"

Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

Film thickness

Specification range	Low	High	Recommended
Dry film thickness	30 micron [1.2 mils]	40 micron [1.6 mils]	30 micron [1.2 mils]
Wet film thickness	68 micron [2.7 mils]	90 micron [3.6 mils]	68 micron [2.7 mils]
Theoretical spreading rate	15 m ² /L [611 sq ft/US gal]	11 m ² /L [448 sq ft/US gal]	15 m ² /L [611 sq ft/US gal]

Application conditions

- Surface temperature must be above 5°C [41°F] during application and curing.
- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.
- Provide adequate ventilation during application and drying.

Relative Humidity:

- Relative humidity must be below 75% during drying and curing.

Application remarks

- Stir well before use.
- The practical consumption factor may vary depending on application conditions, equipment and workmanship.
- Two coats of the topcoat may be necessary to obtain full hiding power.

Topaz Signature Endless Matt

Drying and overcoating

Product compatibility

- Previous coat: Recommended products are: Sealing/ Priming: Hempel's Pro Primer or Hempel's WB Primer or as specified.
- Filling: Hempel's Mastic Filler or Hempel's Interior Filler or as specified.

Drying time

Surface temperature		10°C [50°F]	20°C [68°F]	40°C [104°F]
Surface dry	hours	3	2	1
Through dry	hours	6	4	2

Determined for dry film thickness 30 micron [1.2 mils] at standard conditions, see Hempel's Explanatory Notes for details. Any masking tape used during paint application should be removed while the paint is still in the wet condition.

Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		10°C [50°F]	20°C [68°F]	40°C [104°F]
Atmospheric mild				
Topaz Signature	Min	8 h	4 h	2 h
Endless Matt	Max	Ext*	Ext*	Ext*

Ext*: Depending on the actual exposure conditions, the coated surface is overcoatable for an extended period of time. Contact your local Hempel representative for advice.

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.

Storage

Shelf life

Ambient temperature	25°C [77°F]
Product	24 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. For advice, please consult Hempel.

Storage conditions

- Temperature must not go below 0°C [32°F] during transport and storage.
- The product must be stored in accordance with Safety Data Sheet, label and local regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Additional Certifications and Standards

Topaz Signature Endless Matt

Additional documents

Additional information is available at the Hempel website <https://www.hempel.com/service-and-support/technical-guidelines> or at your local Hempel website:

- Explanatory Notes for Product Data Sheet.
- Application methods.

Scrub resistance tested according to ASTM D2486.
 Heavy metals content tested according to ASTM D3335.
 Acid and alkali resistance tested according to ASTM D543.
 Resistance to household chemicals tested according to ASTM D1308.
 Bacterial resistance tested according to ISO 22196.
 Stain resistance (Washability) tested according to ASTM D4828.
 Fungal resistance tested according to ASTM G21.
 Burnish Resistance tested according to ASTM D6736.
 Water fog resistance tested according to ASTM D1735.
 VOC content tested according to USEPA 24.
 VOC emission tested according to CDPH V1.2.
 Pull-Off Adhesion tested according to ISO 4624.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.